

# TRILITE® AW30

Gaussian Weak Base Anion Exchange Resin, Macroporous

Rev 3. Jan 2023

TRILITE® AW30 is a porous-type WBA exchange resin with a high proportion of weak base groups, making it suitable for use in starch refining and other applications. TRILITE® AW30 exhibits outstanding chemical stability, heat resistance, and mechanical durability. It is supplied in its FB (Free Base) form.

## Physical and Chemical Properties

Matrix	Polystyrene+DVB, Porous	Functional Group	Type 1 (Tertiary Amine)
Ionic Form	Free Base	Total Capacity(eq/ℓ)	1.5 ↑
Shipping Density(g/ℓ)	700	Moisture Retention(%)	48~58
Particle Density	1.05	Uniformity Coefficient	1.6 ↓
Particle Size(μm)	425~1,200	Swelling Rate (FB→Cl <sup>-</sup> , %)	20
Whole Beads(%)	95 ↑		

## Recommended Operating Conditions

Operating Temp(°C)	60 ↓	pH Range	0-7
Bed Depth(mm)	700	Service Flow Rate(m/h)	5~60

## Regeneration

Regenerant	NaOH	Concentration(%)	2~8
Level(g/ℓ)	30~150	Flow Rate(m/h)	2~8
Rinse Requirement(BV)	2~8		

## Applications

TRILITE® AW30 is used for special purification applications such as starch and syrup refining, as it has a high exchange capacity and resistance to organic contamination.

All information contained in brochure is not absolute rather than relative one, created under the controlled environment by Samyang Corporation. Therefore, Samyang Corporation has no legal responsibility with respect to any and all information provided in brochure.

Samyang's TRILITE Ion exchange resins are produced based on the ISO 9001, ISO 14001 certification.  
 Samyang Corporation, 31 Jong-ro 33-gil, Jongno-gu, Seoul, Korea Tel: (02)740-7732~7, Fax: (02)740-7140



<http://samyangtrilite.com>